

## CLAIMS

1. A modified polyolefin resin,  
which is obtainable by graft modifying a propylene-  
5 based random copolymer having a melting point of 50 to  
130°C obtainable by polymerization in the presence of a  
metallocene catalyst, with an unsaturated carboxylic acid  
and/or its derivative, and  
which has a weight average molecular weight of 15,000  
10 to 200,000, a graft weight of the unsaturated carboxylic  
acid and/or its derivative being in the range of 0.2 to 50%  
by weight.
2. A modified polyolefin resin,  
15 which is obtainable by graft modifying a propylene-  
based random copolymer having a melting point of 50 to  
130°C obtainable by polymerization in the presence of a  
metallocene catalyst, with an unsaturated carboxylic acid  
and/or its derivative and with a (meth)acrylic acid ester,  
20 and  
which has a weight average molecular weight of 15,000  
to 200,000, a graft weight of the unsaturated carboxylic  
acid and/or its derivative being in the range of 0.1 to 20%  
by weight, a graft weight of the (meth)acrylic acid ester  
25 being in the range of 0.1 to 30% by weight.
3. An adhesive, comprising the modified polyolefin resin  
according to claim 1 or 2.
- 30 4. A primer, comprising the modified polyolefin resin  
according to claim 1 or 2.
5. A binder for paint, comprising the modified polyolefin

resin according to claim 1 or 2.

6. A binder for ink, comprising the modified polyolefin resin according to claim 1 or 2.

5

7. A polyolefin formed article, comprising:  
a polyolefin substrate, an undercoat layer formed of the modified polyolefin resin according to claim 1 or 2, and a paint layer;

10 wherein the undercoat layer is overlaid on the polyolefin substrate; and

wherein the paint layer is overlaid on the undercoat layer.

15 8. A modified polyolefin resin composition, comprising:  
the modified polyolefin resin according to claim 1 or 2; and an organic solvent.

9. A modified polyolefin resin composition, comprising:  
20 the modified polyolefin resin according to claim 1 or 2; water; and a surfactant,  
the modified polyolefin resin being dispersed in water to have an average particle diameter of not more than 300 nm.

25

30